Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1 - 13 (canceled)

14 (previously presented): An extruded base for an imaging element comprising a matrix polymer and an intercalated clay comprising clay intercalated with polyether block polyamide copolymer, wherein said matrix polymer comprises polyolefin or polyester.

15 (canceled):

16 (previously presented): The extruded base of claim 14 wherein said matrix polymer comprises poly(propylene).

17 (canceled):

18 (previously presented): The extruded base of claim 14 wherein said polyester comprises polyethylene terephthalate.

19 (previously presented): The extruded base of claim 14 wherein said polyester comprises crystalline polyester.

20 (previously presented): The extruded base of claim 14 wherein said polyester comprises amorphous polyester.

21 (canceled):

22 (previously presented): The extruded base of claim 14 wherein said article further comprises compatibilizer.

- 23 (previously presented): The extruded base of claim 22 wherein said compatibilizer comprises polyolefins.
- 24 (previously presented): The extruded base of claim 14 wherein said article has a surface resistivity of less than 10¹³ ohms per square.
- 25 (previously presented): The extruded base of claim 24 wherein said surface resistivity is between 10⁸ and 10¹² ohms per square.
- 26 (previously presented): The extruded base of claim 14 wherein the Young's modulus of the said copolymer and matrix polymer is enhanced by at least 10%.
- 27 (previously presented): The extruded base of claim 14 wherein the Young's modulus of the said copolymer and matrix polymer is enhanced by at least 20%.
- 28 (previously presented): The extruded base of claim 27 wherein said matrix polymer comprises polyolefin and said polyolefin comprises between 20 and 99.9 % by weight of said article.
- 29 (previously presented): The extruded base of claim 14 wherein said clay comprises smectite clay.
- 30 (previously presented): The extruded base of claim 14 wherein said clay comprises synthetic smectite clay.
- 31 (previously presented): The extruded base of claim 14 wherein the ratio by weight of clay to copolymer is between 1:99 and 99:1.
- 32 (previously presented): The extruded base of claim 14 wherein the polyether to polyamide molecular weight ratio is between 5:95 and 95:5.

33 (previously presented): The extruded base of claim 14 wherein said copolymer comprises blocks selected from the group consisting of polyamide 6, polyamide 12, polyethylene oxide, polyethylene glycol, polytetramethylene oxide, and polytetramethylene glycol.

34 (previously presented): The extruded base of claim 33 wherein in said polyether block comprises a structure

$$(--OC_x H_{2x} --)_n$$

wherein x is from 2 to about 8, wherein the alkyl group is straight or branched, and

wherein n is from 2 to about 1000.

35 (previously presented): The extruded base of claim 14 wherein said imaging member comprises a base for a photographic member.

49 (previously presented): The extruded base of claim 14 wherein in said polyamide block comprises the recurring unit represented by the general formula:

--NHCOR¹COHNR² --

wherein R¹ is an alkylene group of at least 2 carbon atoms or arylene having at least 6 carbon atoms; and

R² is selected from R¹ and aryl groups.

$$50-53$$
 (canceled)

54 (new): An extruded base comprising polyether block polyamide copolymer and intercalated clay, wherein said article comprises a base for an imaging member.

55 (new): The extruded base of claim 54 wherein said article has a surface resistivity of less than 10^{13} ohms per square.

56 (new): The extruded base of claim 54 wherein the Young's modulus of the said copolymer is enhanced by at least 10%.

57 (new): The extruded base of claim 54 wherein the Young's modulus of the said copolymer is enhanced by at least 20%.

58 (new): The extruded base of claim 54 wherein said clay comprises smectite clay.

59 (new): The extruded base of claim 54 wherein said clay comprises synthetic smectite clay.

60 (new): The extruded base of claim 54 wherein the ratio by weight of clay to copolymer is between 1:99 and 99:1.

61 (new): The extruded base of claim 54 wherein the polyether to polyamide molecular weight ratio is between 5:95 and 95:5.

62 (new): The extruded base of claim 54 wherein said copolymer comprises blocks selected from the group consisting of polyamide 6, polyamide 12, polyethylene oxide, polyethylene glycol, polytetramethylene oxide, and polytetramethylene glycol.

63 (new): The extruded base of claim 54 wherein said imaging member comprises a base for a photographic member.

64 (new): The extruded base of claim 54 wherein in said polyether block comprises a structure

$$(--OC_x H_{2x} --)_n$$

wherein x is from 2 to about 8, wherein the alkyl group is straight or branched, and wherein n is from 2 to about 1000.

65 (new): The extruded base of claim 54 wherein in said polyamide block comprises the recurring unit represented by the general formula:

--NHCOR¹COHNR² --

wherein R^1 is an alkylene group of at least 2 carbon atoms or arylene having at least 6 carbon atoms; and R^2 is selected from R^1 and aryl groups.